

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

TEST REPORT

Client : B & R Converters NSW Pty Ltd
10 Stonny Batter Road
Minto NSW 2566

Test Number : 20-004716
Issue Date : 22/09/2020
Print Date : 22/09/2020

Sample Description Laminated Hopsack Weave Fabric

AATCC 127-2008
Option 2
(Modified)

Water Resistance Hydrostatic Head

Date of Testing	22/09/2020
Specimen	
1	2100 cm H2O
2	2000 cm H2O
3	2000 cm H2O
4	2100 cm H2O
5	2200 cm H2O
Mean	2080 cm H2O
Gradient	60 mbar/min

Test area : 44.2 cm²

Sample tested with face towards water.

Observation:

Fabric laminate distended during test.

215379

46637

Page 1 of 1

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR